









DEFECTS		GS	SS
Moisture content		20%	20%
Rate of growth		10mm maximum	6mm maximum
Fissures	Not through thickness (ignore those less than half thickness).	Not greater than 1.5m or 1/2 length whichever is lesser.	Not greater than 1m or 1/4 length whichever is lesser.
	Through the thickness.	Not greater than 1m or 1/4 length of the piece whichever is lesser. At ends not greater than 2 x width.	Only permitted at the ends and not greater than the width.
Wane		Not exceeding 1/3	Not exceeding 1/3
Slope of grain		1 : 6 maximum	1 : 10 maximum
Shape		Bow  Not greater than 20mm over 2m	Bow  Not greater than 10mm over 2m
		Cup  Unlimited	Cup  Unlimited
		Spring  Not greater than 12mm over 2m	Spring  Not greater than 8mm over 2m
		Twist  Not greater than 2mm per 25mm width over 2m	Twist  Not greater than 1mm per 25mm width over 2m
Knots	Margin condition	1/3 maximum	1/5 maximum
	No margin condition	1/2 maximum	1/3 maximum
Insect and fungal attack		No active infestation or wood wasp holes	

Brookridge

 Timber



01823 680546



SALES@BROOKRIDGE.CO.UK

A Division of the Brookridge Group